

1. PRODUCT NAME

Gray Guard

2. MANUFACTURER

GMX, Inc. 3800 E. 91st Street Cleveland, OH 44105 Phone: 866-228-7743 Fax: 216-430-3500

3. PRODUCT DESCRIPTION

Gray Guard is a heavy bodied, ready-to-use elastomeric acrylic resin paint. It dampproofs and beautifies all types of exterior and interior masonry surfaces. Acrylic modifiers in Gray Guard compliment the acrylic modifier in the Ultra-Shield below grade waterproofing. Gray Guard will not peel, chip, blister or crack. It is used for both new construction and restoration. It hides rust stains and discolorations, and it is non-fading and washable.

3. PRODUCT ADVANTAGES

- Forms a thick rubber-like blanket of protection
- Protects against moisture
- 100% acrylic elastomeric resin for durability and long life
- Expands and contracts with surface material
- Retains flexibility from -30°F to 160°F
- High solids for better coverage
- Cured elastomeric film is mildew and algae resistant
- Unaffected in accelerated weather monitoring through 15 years of season cycles
- Soap and water cleanup while wet

4. USES

Gray Guard is suitable for application over painted and unpainted surfaces of cement, cinder block, concrete, brick, stone, stucco, tile, plaster and composition board.

5. APPLICATION

Do not attempt to paint over dirt, grease and loose or chalky mortar. Clean the surface as needed and repair loose or chalky mortar as required. Gray Guard is ready to use as is; however, some stirring may be necessary. Stir slowly (preferably with a paddle). It is not necessary to dampen the surface to be painted but slight surface dampness will not impede the bonding properties of Gray Guard . DO NOT ATTEMPT TO COAT HEATED WALL SURFACES.

Gray Guard can be applied by brush, spray, or roller, and the application rate varies according to the porosity of the surface. Apply two coats for best results. DO NOT APPLY GRAY GUARD IF RAIN IS ANTICIPATED WITHIN 6 - 8 HOURS AFTER APPLICATION.

7. TECHNICAL SERVICES

Your local GMX representative is available to assist you in selecting the appropriate product and to provide onsite application assistance. For further information, please contact our Technical Service Dept. at 866-228-7743.

TECHNICAL DATA - Grey Guard

Density @ 77°F (25°C) 10.7 lbs./gal.
Non-Volatile % by weight 51%
Non-Volatile % by volume 35%
Viscosity 120 KU

(Krebs Stormer - ASTM 412)

Elongation

(ASTM 412)

Coverage Approx. 50-100 sq.ft./gal.

100%



© 2013 Garland Industries, Inc.

GMX, Inc. 3800 E. 91st Street Cleveland, OH 44105 Toll Free: 866-228-7743 Fax: 216-430-3500

www.gmxwaterproofing.com