



A Subsidiary of Garland Industries

BoneDry™ RG

DESCRIPTION

BoneDry™ RG is a commercial grade waterproofing membrane designed to be applied with a roller. BoneDry RG is used as a below-grade exterior waterproofing compound and exhibits excellent strength, adhesion, and flexibility. BoneDry RG is a premium grade waterproofing compound used in commercial building construction and can be used for all other types of below-grade waterproofing.

BoneDry RG is designed to be applied with a roller. We recommend that the BoneDry RG be applied to a cured thickness of 40 - 60 mils. It may take several applications to obtain a 40 - 60 mil cured membrane. For detailed application instructions contact GMX at (866) 228-7743.

APPLICATIONS

- Masonry foundations
- Poured foundations
- Pre-cast foundations
- Horizontal waterproofing
- Planters
- Retaining Walls
- Cavity wall air barrier

TECHNICAL DATA

Property	Test Method	Value
Color		Black/Brown
Solids		63% ± 2%
Thickness		40-60 mil dry
Tensile Strength	ASTM D 412	87 psi
Elongation	ASTM D 412	1800%
MVT	ASTM E 96	0.19 gr/hr* sq. ft.
Adhesion to Concrete	ASTM C 834	Exceeds
Shore Hardness	ASTM C 836	75
Crack Bridging	ASTM C 836	Exceeds
Low Temp Flexibility	ASTM C 836	No Cracking
Perm Rating	ASTM C 836	0.38 perms

The information and recommendations discussed in this publication are believed to be correct. The ASTM testing is conducted by an independent accredited laboratory. No statement should be construed as a recommendation for any use, which would violate any patent rights. This document is not a guarantee of a warranty, if approved by GMX, Inc., a performance warranty may be granted.